



Oxford

Item number: 26944



Technical Sheet

Width	approx. 150 cm
Weight	approx. 390 g/m ²
Repeat	no repeat
Composition	100% Wolle
Flame retardant	DIN 4102/B2, DIN EN 1021 Teil 1, DIN EN 1021 Teil 2, BS 5867 TYP B, IMO Res. A471 (XII), IMO Res. A652 (16), Flame-resistance is dependant of foam that is used.
Lightfastness	note 5-6
DIN EN ISO 105-B02	
Fastness to Washing 40°	note 4-5
DIN EN ISO 105-C10	
Fabric relaxing washing 40°C	warp approx. +/-3%, weft approx. +/-1,5 %
DIN EN ISO 6330/DIN EN ISO 5077	
Fabric relaxing dry cleaning	warp approx. +/-1%, weft approx. +/-1 %
DIN EN ISO 3175-1	
Rub Fastness	dry: note 5, wet: note 4-5
DIN EN ISO 105-X12	
Scrub resistance Martindale	approx. 30000 rubs
DIN EN ISO 12947-2 / DIN EN 14465-2006	
Pilling	note 2-3 at 2000 rubs
DIN EN ISO 12945-2	
Sound absorption factor	0.85
Sound absorption class	B
Care	

State: 20.07.2015

The above technical data are average values. These values only describe the technical characteristics and the chemical composition of the delivered goods. Warranties are not given.